

Ficha Técnica

Esmalte Laca Uretanada



Ventajas

- Great fineness.
- Soft touch.
- Lacquered appearance.
- Excellent protection of ferrous surfaces.

Descripción

High performance lacquer enamel with polyurethane and anticorrosive additives with which to obtain satin finishes of great fineness, soft touch, lacquered appearance and excellent protection of ferrous surfaces. It is resistant to friction, scratches and chemical agents typical of household cleaners.

Certificados de empresa



Datos técnicos

Datos de identificación del producto

Color	White, black and color chart
Aspecto	Satin



Naturaleza	Urethane alkyd resins.
Peso específico	1,10 - 1,14 Kg/L (depending on color)

Datos de aplicación del producto

Rendimiento	12 -14 m2 /L for a 40 -50 microns layer
Diluyente	Disolvente Sintético Jafep
Repintado	24 h
Secado	4 - 6 hours

Prestaciones finales

Resistencia al frote en húmedo	Very washable
--------------------------------	---------------

Dónde aplicarlo

In exterior and interior. As protection of wood, metal and other surfaces treated properly.

Modo de empleo

GENERAL RULES: Product practically ready to use. It can be thinly diluted to improve the brochability. Stir the contents of the container well. Surfaces must be clean, free of rust, grease, dust, etc. If it is already painted, check that it is in good condition and correctly adhered. It can be applied with a brush of fine hair, roller or gun and always in thin layers and respecting the time of repainting. The temperature of application, humidity, thickness and type of support have associated changes in the drying time and the theoretical yield. In general, do not paint below 5°C, with relative humidity above 80%, excessive sun, strong wind or risk of rain. In any case, you must apply 2 hands indoors and even 3 hands outside.

UNPAINTED SURFACE

Iron or steel: Apply first Imprimación Antioxidante Jafep.

Wood: Sand and apply Selladora Sintética or Multiusos Jafep.

PAINTED SURFACE

Iron and steel: If it is in good condition, give a superficial cleaning and proceed as an unpainted surface. Otherwise, the paint should be removed, for example with Quitapinturas Gel Jafep and proceed to normal painting as if it were an unpainted surface.

Wood: If it is in good condition, a previous sanding is recommended. Otherwise, its total elimination is better, and proceed



as on unprepared surfaces.

Formatos

Metalic cans of: 750 mL and 4 L



Atención al Cliente

967 44 05 96

atencionalcliente@jafep.com



Servicio Técnico

dpto_tecnico@jafep.com



ARGENTINA DUBAI ESPAÑA MARRUECOS POLONIA UCRANIA

www.jafep.com
jafep@jafep.com