

Ficha Técnica

Swimming Pool Water-Based Emulsion Paint



Acrylic plastic paint for swimming pools

Versión: 29/08/2022



Descripción

Matte plastic paint, made with special acrylic resins of great resistance and durability, for the conditions to which will be subjected.

Propiedades

- Special water resistance
- Good strength and durability
- Low levels of emissions and pollution
- Simple application
- Fast drying and short recoating times

Certificados de empresa





Datos técnicos

Datos de identificación del producto

Color	White and Blue
Aspecto	Matt
Naturaleza	Special acrylic resins
Peso específico	1.50 g/ cm ³

Datos de aplicación del producto

Rendimiento	6 - 8 m ² /kg.
Diluyente	Water
Repintado	After 6 hours
Secado	30 minutes

Dónde aplicarlo

Specially formulated for cement or concrete pools due to its special resistance to water, alkalis and acids.

In pools with tiles or mosaic, it can be used if we use the Water-based epoxy primer as a bonding bridge of two components.

Precauciones

- Do not apply at temperatures below 5°C or above 30°C.
- Do not apply with risk of frost or rain.
- Do not apply in conditions of strong winds or in direct sunlight.
- Avoid using different batches in the same cloth or, failing that, mix the current can with the next one at 50% to reduce the normal differences between batches.
- Allow at least 15 days to pass before filling the pool.



Productos relacionados

SELLACRYL

Modo de empleo

Cement and concrete surfaces:

- New Floor:

Allow at least 30 days to elapse before being painted for complete setting. The surface must be porous and the lime milk must be removed from the setting. Before proceeding with painting, the support must be free of damp, clean, dry and without the presence of rust, grease or salt.

If there are traces of dirt or the pore has to be opened, whether it is a new surface or not, proceed with the Following way:

1. Apply sulfumán or diluted acids 10-15% in water and leave to act for 15 minutes.
2. Rinse with plenty of water to neutral pH.
3. Wait 24-48 hours for it to dry properly.

Once the surface is prepared, we will begin by priming the support. For this, a first layer of Sellacryl diluted with Thinner for water-based paints and enamels in a 4:1 ratio, respectively. As an alternative, it you could apply a first coat of Water-Based Paint diluted 25% with Thinner for water-based paints and enamels. Wait 8 hours to repaint.

Apply two coats of Piscinas al Agua directly after use or diluting a maximum of 5% with our Diluent for water-based paints and enamels, leaving 6 hours to dry between coats.

On old painted surfaces:

- With paints in good quality condition:

Wash and sand lightly, putty if necessary and apply afterwards. In addition, an adhesion test is recommended to ensure material compatibility. For this it must paint a small non-visible area, let it dry for two weeks and try scraping or scratching to see if the adhesion is adequate.

- With paintings in poor condition:

Remove and proceed as a new surface. If alkalinity is detected on the support, must correct.

- Tile or mosaic surfaces:

The surface must be prepared properly, sand the area to be prepared and leave it free of dust, clean and dry. One time prepared, apply the Water-based Epoxy Primer diluted 30% with the Diluent for water-based paints and enamels.

Let dry for 24 hours to repaint. Apply two coats of Piscinas al Agua to the use or diluting a maximum of 5% with

the Thinner for water-based paints and enamels, leaving 6 hours between coats.



It is recommended to allow at least 15 days to elapse before filling the pool.

We remind you that the growth of algae or mold can be a purification problem.

Carta de colores

White & Blue

Formatos

Containers of: 4 L; 15L

Herramienta (Descripción)

Brush, roller, spray or airless



Atención al Cliente

967 44 05 96

atencionalcliente@jafep.com



Servicio Técnico

dpto_tecnico@jafep.com



100% Reciclado

