

Ficha Técnica

BS Acrylic Enamel direct to Galvanized and other Metals



Solvent-based acrylic enamel.

Versión: 19/04/2023



Ventajas

- Ideal for galvanized.
- High hardness.

Descripción

Solvent-based acrylic enamel, glossy pigmented, with very good adhesion on all types of metals and excellent on single-hand galvanized iron. It has good resistance to light, weather and corrosion. High hardness and good flexibility.

Certificados de empresa



Datos técnicos

Datos de identificación del producto



Color	White, Black, Aluminum 9006, Red 3005, Green 6005, Blue 5017 and others on request.
Aspecto	Gloss
Naturaleza	Thermoplastic acrylic
Peso específico	1.00 - 1.15 gr./cm ³

Datos de aplicación del producto

Herramienta	Spray Gun - Airless
Rendimiento	8 - 10 m ² /litre
Diluyente	White Spirit Jafep Solvant
Repintado	24 hrs
Secado	30 minutes

Dónde aplicarlo

Especially recommended for painting galvanized sheet metal, but with very good results on aluminium, copper, iron, galvanized sheet metal, etc.

Precauciones

- Do not apply at temperatures below 5°C, nor above 30°C, nor below dew point. The temperature of the product and that of the support must also be within this temperature range for said application.
- Do not apply with risk of frost or rain.
- Do not apply in conditions of strong winds or in direct sunlight.
- Avoid using different batches in the same cloth or, failing that, mix the current bottle with the next one at 50% to reduce the normal differences between batches.

Modo de empleo

Direct application product without prior dilution in general, although when applying by spray or "airless", which is the most recommended process, we must adjust the viscosity for a better application. The support to be painted must be free of dust, grease, rust, etc.

* Special roller: It has been verified that there are rollers on the market with which to apply our BS Acrylic Enamel, such as the "Velourex" roller. However, due to the characteristics of some acrylic resins, although we could apply the first coat well with a roller, it is almost impossible to apply the second, since the roller tends to stick to the first.



Almacenamiento

- In its original closed container, at non-extreme temperatures and humidity.
- Keep away from direct sunlight.
- Recommended maximum since manufacture: 2 years.

Formatos

Metal containers: 750 ml & 4 Liters



Atención al Cliente

967 44 05 96

atencionalcliente@jafep.com



Servicio Técnico

dpto_tecnico@jafep.com

