Ficha Técnica

Ox Anti-corrosive Alkyd Enamel "Forge Effect"





Ventajas

- Good elasticity
- Exterior durability.

Descripción

Alkyd enamel, pigmented with micaceous iron oxide of different granulometries and anticorrosive additives that provide a protective as well as decorative finish to any iron surface.

Certificados de empresa



Datos técnicos

ARGENTINA

Datos de identificación del producto

| Color | Black, Grey |
|------------|--------------|
| Aspecto | Forge Effect |
| Naturaleza | Alkyd |

DUBAI





| Peso específico | $1,65 \pm 0,1 \text{ g/cm}^3$ |
|-----------------|-------------------------------|
| Viscosidad | Thixotropic |

Datos de aplicación del producto

| Herramienta | Brush, roller, spray (with appropriate nozzles) or airless |
|----------------|--|
| Espesor mínimo | 110 dry microns (2 coats) to achieve correct anti corrosive protection |
| Rendimiento | 8-12 m ² /L/Coat |
| Diluyente | Jafep White Spirit |
| Repintado | 24 hours |
| Secado | 4-6 hours |

Dónde aplicarlo

Suitable for: fences, streetlights, railings, chairs, tables, etc.

Precauciones

- Do not apply at temperatures below 5 °C or above 30 °C.
- Do not apply at risk of frost or rain.
- Do not apply in strong wind conditions or under direct sun.
- Avoid using different batches in the same cloth or, failing that, mix the current jar with the next one 50% to reduce the normal differences between batches.

Productos relacionados

OX Solvent

Modo de empleo

Surfaces will be clean, dry and primed when necessary.

If the surface is new, it is advisable to apply an antioxidant primer to complete the protection.

On already painted surfaces, we will also sand until the previous paint is nuanced.

Physical properties such as drying, repainting, performance, etc., may undergo notable variations depending on temperature, humidity, application method or thickness of the applied film.



*IMPORTANT: It is essential to apply a minimum thickness of 110 dry microns (0.11 mm) to achieve correct antioxidant protection in medium aggressive environments. This thickness is achieved by applying two coats. Special care must be taken in corners, joints and welds.

Almacenamiento

- In its original closed container, at non-extreme temperature and humidity.
- Keep away from direct sunlight.
- Maximum recommended since manufacturing: 2 years.

Formatos

Containers: 750 ml & 4 L





