

Ficha Técnica

Ox Anti-Corrosive Alkyd Enamel "Martelé"



Descripción

Alkyd enamel with antioxidant properties with a "hammered" or hammered finish that provides effective protection while decorating and hiding imperfections on any iron surface.

Propiedades

- Antioxidant.
- Outdoor durability.

Certificados de empresa



Datos técnicos

Datos de identificación del producto



Color	Silver Grey, Grey, Copper and Dark Green
Aspecto	Gloss Martelé (Hammered effect)
Naturaleza	Alkyd

Datos de aplicación del producto

Herramienta	Spray Gun or Airless
Rendimiento	10-12 m ² /L/Coat
Diluyente	Jafep White Spirit
Repintado	24 hours
Secado	1 hour

Prestaciones finales

Resistencia al frote en húmedo	5
--------------------------------	---

Dónde aplicarlo

It can be applied on any iron surface. This product is not recommended for exterior horizontal surfaces without adequate water evacuation since if stagnant water remains, hydrolysis (whitish stains) may occur.

**IMPORTANT: The silicones contained in this product are incompatible with most other paints (e.g. appearance of craters on the surface). The application and cleaning of utensils should be carried out with the greatest possible isolation.*

Precauciones

- Do not apply at temperatures below 5 °C or above 30 °C.
- Do not apply at risk of frost or rain.
- Do not apply in strong wind conditions or under direct sun.
- Avoid using different batches in the same cloth or, failing that, mix the current jar with the next one 50% to reduce the normal differences between batches.

Productos relacionados

SYNTHETIC SOLVENT



Modo de empleo

Correctly stir the contents in the container, diluting appropriately according to applications.

Surfaces will be clean, dry and primed when necessary.

If the surface is new, it is advisable to apply an antioxidant primer to complete the protection.

On already painted surfaces, we will also sand until the previous paint is nuanced.

The shape of the hammering depends on several factors such as the amount of dilution made and the pressure and flow rate of the gun.

Almacenamiento

- In its original closed container, at non-extreme temperature and humidity.
- Keep away from direct sunlight.
- Maximum recommended since manufacturing: 2 years.

Formatos

Containers: 750 ml & 4L



Atención al Cliente

967 44 05 96

atencionalcliente@jafep.com



Servicio Técnico

dpto_tecnico@jafep.com

