

Ficha Técnica

Rugosil

Textured stone coating

Versión: 31/10/2023



Descripción

Rough stone coating made with emulsion resins and pigments with high resistance and light fastness, which provide an elastic and waterproof finish but at the same time resistant to adverse weather agents. It has a good filling power that hides the defects of the plaster and an excellent cut with a rough finish of great whiteness. Ease of application. This product contains preservative additives for film protection.

Propiedades

- Finish resistant to adverse weather agents
- Good filling power, hides plastering defects.
- Contains anti-mold preservatives

Certificados de empresa



Datos técnicos

Datos de identificación del producto

Color	White
Aspecto	Matt Textured
Naturaleza	Emulsion copolymers
Peso específico	1,55 gr/cm ³

Datos de aplicación del producto

Herramienta	Brush, roller, drop gun or zip line
Rendimiento	1-1,5 m ² /L/Coat
Diluyente	Thinner for water-based paints and enamels
Repintado	6 hours
Secado	30 minutes

Prestaciones finales

Resistencia al frote en húmedo	3,5
--------------------------------	-----

Dónde aplicarlo

Stone coating suitable for the protection of facades, interior backyards, in medium climate environments. The studied granulometry of its components covers surface defects, small cracks, pores, etc.

Precauciones

- Do not apply at temperatures below 5 °C or above 30 °C.
- Do not apply at risk of frost or rain.
- Do not apply in strong wind conditions or under direct sun.
- Avoid using different batches in the same cloth or, failing that, mix the current jar with the next one 50% to reduce the normal differences between batches.

Modo de empleo



It can be applied with a brush, roller or drip gun and zip line. The surfaces must be clean, dry, free of rust, saltpeter, humidity, etc. If the surface is new, it will be primed with a layer of paint diluted with 10 - 15% water, followed by another regular layer to achieve the desired effect.

If the surface is old, already painted, efforts will be made to scratch and completely clean the one that is in poor condition.

Almacenamiento

- In its original closed container, at non-extreme temperature and humidity.
- Keep away from direct sunlight.
- Maximum recommended since manufacturing: 2 years.

Formatos

Containers: 15 L



Atención al Cliente

967 44 05 96

atencionalcliente@jafep.com



Servicio Técnico

dpto_tecnico@jafep.com



Compromiso Medioambiental y Social Jafep

ARGENTINA

DUBAI

ESPAÑA

MARRUECOS

POLONIA

UCRANIA



www.jafep.com
jafep@jafep.com